

Analysis of special fuel parameters of wood chips

Results for determination of fuel parameter

	Chips (pine)	
1.	Moisture content of dry chips, %	40%
2.	Ash content, %	0.37-0.39
3.	Net calorific value, KJ/kg	18800
4.	Thickness, mm	Till 30
5.	Length, mm	5-50